

Product Information

Electronic Protection System

**Polybutadiene Potting/Encapsulation Resin**

**Bectron<sup>®</sup> PB 3200**

Hardener Bectron PH 4917

**ELANTAS Europe GmbH**  
Grossmannstr. 105  
20539 Hamburg  
Germany  
Tel +49 40 78946 0  
Fax +49 40 78946 276  
bectron.elantas.beck@altana.com  
www.elantas.com

### Product description

Bectron<sup>®</sup> PB 3200 with Hardener Bectron<sup>®</sup> PH 4917 is a 2 component system to produce a very flexible casting. It is based on polyurethane with polybutadiene to provide good flexibility at very low temperature and superior resistance properties

The mixed product has very low viscosity for rapid high volume processing.

### Areas of application

Bectron<sup>®</sup> PB 3200 is suitable for many applications, particularly where severe thermal shock stability is required and also where good protection against humidity aggressive chemicals shock and vibration are required.

Its flexibility allows mechanical removal for rework or to produce a cast of the unit potted.

### Properties of the cured material

The cured material has very high elasticity and flexibility.

It remains flexible at very low temperatures.

Low glass transition temperature T<sub>g</sub>

Satisfies the requirements of ROHS

### Storage

Bectron<sup>®</sup> PB 3200/PH 4917 is supplied in a one pot "combi-container" which should be kept well closed at normal temperatures.

Once opened the follow the processing suggestions below. The product can not be resealed.

### Processing suggestions

When the container seal is broken the hardener is released into the resin. The mixture should be well stirred for a homogenous mixture before use. Bectron<sup>®</sup> PB 3200/Hardener Bectron<sup>®</sup> PH 4917 is a low viscosity system which can be applied in a continuous process with conventional mixing and dispensing equipment.

For manual batch application thorough mixing of small quantities is recommended in view of the short pot life and exothermic reaction which will cause a rise in temperature during curing.

Recommended temperature for curing is:

- Minimum 5°C, preferably above 15°C
- Complete curing requires 24 hours.

To ensure satisfactory adhesion on the PCB surface the following should be checked:

- Use of residue-free flux
- ensure dry surfaces
- Check compatibility of the coating resin with the solder resist and solder paste.

**Table 1 - Properties of materials as supplied**

Property	PB 3200	PH 4917	Units
Colour	White, milky	Yellow-brown	
Viscosity 25°C DIN 53019	450 ± 150	150 ± 50	mPa.s
Density 20°C DIN EN ISO 2811-1	1.06 ± 0.05	1.14 ± 0.05	g/cm <sup>3</sup>
Shelf Life	6	6	Months

**Table 2 - Properties of mixture**

Mixing Ratio			
Bectron® PB 3200 : Hardener Bectron® PH 4917	weight	100:18	Parts
Viscosity DIN 53019	25°C	900 ± 150	mPa.s
Process time (200g Mixture)	25°C	20	Min

**Table 3 – Thermal Properties of cured compound**

Property	Condition	Value	Units
Thermal Conductivity DIN 52613	23°C	0,28 ± 0,02	W/m.K
Glass transition temperature IEC 61006		-50	°C

**Table 4 - Mechanical properties of cured compound**

Property	Condition	Value	Units
Density DIN 16945	20°C	1.06 ± 0.05	g/cm <sup>3</sup>
Hardness DIN 53505		30 ± 10	Shore A
Elongation at break DIN 53455		50	%

**Table 5 – Dielectric properties of cured compound**

Property	Condition	Value	Units
Volume resistivity DIN 60093	20 °C	10 <sup>13</sup>	Ω • cm
Surface resistance DIN 60093	20 °C	3 x 10 <sup>13</sup>	Ω
Tracking resistance IEC 60112		> 600 M	CTI

**Table 6 - Chemical properties of cured compound**

Property	Condition	Value	Units
Water absorption	4 days RT	1.3	%

The Our advice in application technology given verbally, in writing and by testing corresponds to the best of our knowledge and belief, but is intended as information given without obligo, also with respect to any protective rights held by third parties. It does not relieve you from your own responsibility to check the products for their suitability to the purposes and processes intended. The application, usage and processing of the products are beyond our reasonable control and will completely fall into your scope of responsibility. Should there nevertheless be a case of liability from our side, this will be limited to any damage to the value of the merchandise delivered by us. Naturally, we assume responsibility for the unobjectionable quality of our products, as defined in our General Terms and Conditions