

Product Information

Electronic Protection System

Polybutadiene Potting/Encapsulation Resin

Bectron[®] PB 3251

Hardener Bectron PH 4918

ELANTAS Europe GmbH
Grossmannstr. 105
20539 Hamburg
Germany
Tel +49 40 78946 0
Fax +49 40 78946 276
bectron.elantas.beck@altana.com
www.elantas.com

Product description

Bectron® PB 3251 with Hardener Bectron® PH 4918 is a 2 component system to produce a resilient compound suitable for potting and casting. It is based on polybutadiene with polyurethane & filled to provide strength with flexibility at low temperature and superior resistance properties. It is resistant to organic and inorganic solvents with good adhesion. It is solvent free and does not damage components on the board

Areas of application

Bectron® PB 3251 is suitable for many potting applications needing stability to thermal shock. It is ideal for casting whole PCB to give where good protection against humidity aggressive chemicals shock and vibration are required.

Properties of the cured material

The cured material has high elasticity with flexibility and strength at low temperatures.
Low glass transition temperature T_g

Satisfies requirements of ROHS

Storage

Bectron® PB 3251 should be kept in closed containers at normal temperatures.
Hardener Bectron® PH 4918 is moisture sensitive and containers must be well sealed and stored below +40 °C. Opened containers should be re-sealed as soon as possible.

Processing suggestions

Bectron® PB 3251/Hardener Bectron® PH 4918 is a viscous system which can be applied in a continuous process with conventional mixing and dispensing equipment.

For manual batch application thorough mixing of the 2 components is essential and care is needed to avoid air bubbles. Pot life is about 20 minutes. The viscosity of Bectron® PB 3251 can be reduced by heating to 60 °C but this will reduce the pot life.

Recommended curing is:

- At Room Temperature 48 hours
- AT 60 °C cured in 2 hours.

Final properties after (e.g. Hardness):

- 20 h at 80°C
- 6 weeks at Room Temperature

To ensure satisfactory adhesion on the PCB surface the following should be checked:

- Use of residue-free flux
- ensure dry surfaces
- Check compatibility of the coating resin with the solder resist and solder paste.

Table 1 - Properties of materials as supplied

Property	PB 3251	PH 4918	Units
Colour	Black	Transparent, colourless	
Viscosity, 23°C, D=3 s ⁻¹ , DIN 53019	10,000± 2,000	1,200 ± 300	mPa.s
Density, 20°C, DIN EN ISO 2811-1	1.27 ±.005	1.16 ±.005	g/cm ³
Shelf Life	6	6	Months

Table 2 - Properties of mixture

Mixing Ratio			
Bectron [®] PB 3251 : Hardener Bectron [®] PH 4918	weight	100 : 33	Parts
Viscosity DIN 53019	25°C	15000 ± 3000	mPa.s
Process time	25°C	20	min

Table 3 – Thermal Properties of cured compound

Property	Condition	Value	Units
Operating Temperature range		-60 to +150	°C
Glass transition temperature		-63	°C

Table 4 - Mechanical properties of cured compound

Property	Condition	Value	Units
Density DIN 16945	20°C	1.27 ± 0.05	g/cm ³
Hardness ISO 868		80 ± 10	Shore A
Elongation to break DIN 53455		200	%

Table 5 – Dielectric properties of cured compound

Property	Condition	Value	Units
Volume resistivity VDE 0303 Part 2 After 7 days water immersion	23 °C	1.9 x 10 ¹⁴ 7.4 x 10 ¹³	Ω • cm
Tracking resistance IEC 60112	23 °C	>600	CTI

Table 6 - Chemical properties of cured compound

Property	Condition	Value	Units
Water absorption DIN 53495	4 days RT	0.3	%

The Our advice in application technology given verbally, in writing and by testing corresponds to the best of our knowledge and belief, but is intended as information given without obligo, also with respect to any protective rights held by third parties. It does not relieve you from your own responsibility to check the products for their suitability to the purposes and processes intended. The application, usage and processing of the products are beyond our reasonable control and will completely fall into your scope of responsibility. Should there nevertheless be a case of liability from our side, this will be limited to any damage to the value of the merchandise delivered by us. Naturally, we assume responsibility for the unobjectionable quality of our products, as defined in our General Terms and Conditions